

# SULFEX® YELLOW

## General Inquiries

### North & South America

Tel: 1-800-828-1666

### Europe

Tel: +44(0)161-848-0271

info@washingtomills.com

www.washingtomills.com

## Washington Mills

### North Grafton, Inc.

P.O Box 428

20 North Main Street

North Grafton, MA 01536

Tel: 508-839-6511

Fax: 508-839-7675

Email: info@washingtomills.com

## Washington Mills

### Electro Minerals Corp.

P.O Box 423

1801 Buffalo Avenue

Niagara Falls, NY 14302

Tel: 716-278-6600

Fax: 716-278-6650

Email: info@washingtomills.com

## Washington Mills

### Electro Minerals Corp.

P.O Box 1002

7780 Stanley Avenue

Niagara Falls, Ontario L2E 6V9 Canada

Email: info@washingtomills.com

## Washington Mills

### Tonawanda, Inc.

1000 E. Niagara Street

Tonawanda, NY 14150

Email: info@washingtomills.com

## Washington Mills

### Electro Minerals Ltd.

Mosley Road, Trafford Park

Manchester M17 1NR England

Email: info@washingtomills.com

## Washington Mills Hennepin, Inc.

13230 Prairie Industrial Parkway

Hennepin, IL 61327

Email: info@washingtomills.com

## Washington Mills AS

NO-7300

Orkanger, Norway

Email: wmas@washingtomills.no

## DESCRIPTION

SULFEX® YELLOW, distributed by Washington Mills, is prepared from carefully selected pure monocristallic iron pyrites (FeS<sub>2</sub>). SULFEX® YELLOW consists of finely grained Pyrite crystal splinters, which increases the thermal conductivity, the tensile strength, and the porosity of resin-bonded grinding wheels and cut off wheels.

SULFEX® YELLOW improves durability and performance of organic bonded abrasives by reducing the temperature in the contact zone or the work piece and cut off / grinding wheel.

## APPLICATIONS

SULFEX® YELLOW is used as a grinding-active filler in resin-bonded grinding wheels and cut off wheels, brake linings, etc. It can be used alone or in combination with other active fillers in organic bonded abrasives.

## TYPICAL CHEMICAL ANALYSIS\*

S	50% +/- 2%
Fe	44% +/- 2%

\* SULFEX® yellow is produced out of natural minerals and changes in the compositions of the raw material can occur, these technical data are to be seen as typical values.

## SAFETY REMARKS

Consult appropriate MSDS.

## TYPICAL PHYSICAL PROPERTIES

Color	Powder dark grey to black
Bulk Density	2.2 min to 2.5 max 9/cm <sup>3</sup>
pH	3 to 6
M. Volatile 105°C	0.20%

## LASER GRANULOMETRY

	% Passing
D10	15 µm max
D50	125 µm max
D90	300 µm mx

This product information is NOT a specification. It is offered in good faith only as a general description of the product. **Washington Mills makes no warranty of merchantability or of fitness for any particular purpose.** The product chemistry and other characteristics may vary or contain trace elements not specifically listed. If your intended application for this product is so critical that relatively minor variations in chemistry or physical properties could cause problems or damage to your process or product, please contact our office for further assistance.